

Glyptal Inc.

305 Eastern Avenue
Chelsea, Massachusetts 02150

Telephone (617) 884-6918
Fax (617) 884-8376

PRODUCT DATA SHEET 86009

DESCRIPTION

GLYPTAL 86009 ALUMINUM SILICONE BAKING ENAMEL is a ready-mixed aluminum pigmented silicone resin product designed for high-temperature applications. It provides a durable protective coating on metal surfaces subjected to temperatures of 400-1200 °F. 86009 is suggested as a finish for ovens, jet engines, or other metal surfaces needing protection during or after high-temperature exposure. Optimum results are obtained by applying multiple thin (0.2-0.5 mil) coats.

WET SAMPLE

Coverage (Theoretical)	589 ft ² /gal
Flashpoint, cc/pm	81 °F
Weight	8.1-8.4 lb/gal

APPLICATION

Substrate	Phosphatized Steel
Method	Spray
Reduction	Use as supplied
Clean-up Solvent	Xylene
Dry Film Thickness	0.2-0.5 mils

CURE

Bake Time	60 min
Bake Temperature	200 °C

DRY FILM PROPERTIES

Color	Aluminum
Gloss, 60°	
Pencil Hardness	2H-3H
Flexibility	Excellent
Impact Resistance	
Direct	60 in. lb.
Indirect	60 in. lb.
Adhesion, Cross Hatch	Excellent

In as much as Glyptal, Inc. has no control over the use to which others put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material and the compositions described herein should make his or her own tests to determine the materials' suitability for his or her own particular use. Statements concerning possible or suggested uses of the material described herein are not to be construed as constituting a license under any Glyptal patent covering such use or as recommendations for use of such materials in the infringement of any patent.