

Glyptal Inc.

305 Eastern Avenue
Chelsea, Massachusetts 02150

Telephone (617) 884-6918
Fax (617) 884-8376

PRODUCT DATA SHEET C1800

DESCRIPTION

GLYPTAL C-1800 is designed as a quick-dry, high viscosity gasket seal. The C-1800 red enamel is an excellent protective coating suitable for almost all types of equipment where oil, moisture, and acid resistance as well as good weatherability are desired. It has superior thermal resistance. C-1800 is also very useful in a variety of pipe-thread compound, gasket adhesive, vacuum system sealer, etc.

WET SAMPLE

% Vol. Solids	53 +/- 2
% Wt. Solids	
Viscosity	4000-4400 cps
Fineness of Grind (Hegman)	3 minimum
Flashpoint, cc/pm	
Weight (avg.)	12.2 lb/gal
Coverage (1 mil dry film thickness)	851 ft ² /gal

APPLICATION

Reduced viscosity	Use at package viscosity
Method	Dip or brush

CURE

Flash Time, min	N/A
Tackfree Time	20-30 min

DRY FILM PROPERTIES

Color	Red Iron Oxide
Gloss, 60°	15

In as much as Glyptal, Inc. has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each other user of the material and the compositions described herein should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the material described herein are not to be construed as constituting a license under any Glyptal patent covering such use or as recommendations for use of such materials in the infringement of any patent.